# **TFT™ Perfluoropolyether (PFPE) Teflus® PE Series**

PET Series (Thermal Conduction)	PEV Series ( <u>V</u> acuum Pumps)	PES Series (Vapor Phase <u>S</u> oldering)		
Teflus <sup>®</sup> PET	Teflus <sup>®</sup> PEV	Teflus <sup>®</sup> PES		
PET-55 ~ PET-270	PEV-L1 ~ PEV-L4	PES-200 ~ PES-260		
PEI-33 ~ PEI-270	PEV-H1 ~ PEV-H4	FL3-200 ~ FL3-200		
PEG Series (General Purpose)	PEL Series ( <u>L</u> ubricant oil)	PEA Series (Processing <u>A</u> dditive)		
Teflus <sup>®</sup> PEG	Teflus <sup>®</sup> PEL	Teflus <sup>®</sup> PEA		
PEG-1 ~ PEG-5	PEL-5 ~ PEL-520	PEA-1 ~ PEA-3		

## Perfluoropolyether (PFPE)

TFT LIMITED perfluoropolyether (PFPE) is synthesized by the polymerization of hexafluoropropylene monomer (HFP,  $CF_3CF=CF_2$ ) and oxygen, and a colorless and transparent liquid is obtained after post-treatment.

Chemical structure:

$$(CF_3)$$
 $(CF - CF_2 - O)_n + CF_2 - CF_2 - O)_m + CF_2 - O)_k$ 

#### **Product Features:**

- > For most highly corrosive chemicals, such as strong acids, peroxides, etc., it has excellent chemical inertness.
- > It has the characteristics of high density, low surface tension, low volatility, non-combustibility, good insulation, good lubricity, etc., and has good compatibility with plastics, rubber and metals.
- > It is often used as a heat transfer fluid for many working conditions and as a lubrication use, suitable for high temperature and harsh working environments.
- > In the absence of an effective catalyst, PFPE remained stable in the range of 270°C-300°C, even in the presence of oxygen. Its decomposition temperature can reach 350°C-410°C.

#### Types, grades and applications:

Туре	Grade	Application				
<u>T</u> hermal Conduction	Teflus <sup>®</sup> PET	Used in coolant or heat transfer fluid in chemical, semiconductor, nuclear, pharmaceutical and other industries.				
<u>V</u> acuum Pumps	Teflus <sup>®</sup> PEV	Used as vacuum pump oil to meet the requirements of vacuum pumps for the highly clean electronics indus Vacuum mechanical pumps for the production of semiconductors using ion etching, LPCVD and plasma cult technologies; Vacuum pumps (rotary vane pumps, molecular pumps, diffusion pumps, etc.) used in environments where corrosive gases are present.				
Vapor Phase <u>S</u> oldering	Teflus <sup>®</sup> PES	Used as vapor phase soldering fluid in the vapor phase soldering (VPS)process, the latent heat of condensation of perfluoropolyether oil vapor is used to melt the solder.				
<u>G</u> eneral Purpose	Teflus <sup>®</sup> PEG	Low viscosity perfluoropolyether can be used as heat transfer fluid, electronic cleaning fluid, electronic reliability test fluid, vapor phase welding fluid, mainly suitable for cleaning of electronic products, heat transfer, testing and welding of electronic products, and can also be used in other chemical-resistant occasions; High viscosity perfluoropolyether can be used as lubricating oil, used in oxygen, fluorine, chlorine, hydrogen and other gas compressors, transfer pump lubrication, can also be used as vacuum pump oil, to meet the requirements of vacuum pumps for high cleanliness electronics industry. It can be used as a polymer processing aid to improve the fluidity and self-lubrication of polymers, reduce wear and improve scratch resistance.				
<u>L</u> ubricant Oil	Teflus <sup>®</sup> PEL	Mainly used in chemical, electronic, machinery, aerospace, nuclear industry and other fields, used in oxygen, fluorine, chlorine, hydrogen and other gas compressors, lubrication of transfer pumps, etc.; It is used for the lubrication of hard disks and other magnetic recording media on computers and other instruments; as a lubricant for high temperature and chemically stable porous metal bearings, conveyor belts, paper and textile machinery; for the lubrication of rocket nozzles; for lubrication of missile launch systems; lubrication for anti-lock braking systems; Used for lubrication in the nuclear industry, etc.				
Polymer Processing <u>A</u> dditive	Teflus <sup>®</sup> PEA	As a polymer processing aid to improve process ability (e.g.improved flow ability, extrusion rate and mold release, reduced melt viscosity, reduced die build-up) and improved polymer properties (e.g. enhanced self-lubrication, reduced wear, improved scratch resistance). It can be used for acetal, nylon 6, nylon 12, thermoplastic polyurethane (TPU), SEBS, thermoplastic elastomer (TPE), etc.				

## Perfluoropolyether (General Purpose) Teflus® PEG

#### **Product Features:**

- > Zero ozone depletion.
- > Good compatibility with various rubbers.
- > Good viscosity index, low pour point: can be used in a wide temperature range.
- > Excellent thermal stability, chemical stability, solvent resistance (including polar and non-polar solvents), radiation resistance, weather resistance.
- > Non-flammable in any circumstances. No flash point, no ignition point, no spontaneous ignition point, and will not burn in the presence of oxygen

#### **Product Performance:**

Property	Test Method	Unit	Technical Standards				
			G-1001	G-1002	G-1003	G-1004	G-1005
Appearance	Visual Check	-/	Colorless transparent liquid				
Density (20°C)	GB/T 29617	g/cm <sup>3</sup>	1.72-1.80	1.80-1.86	1.86-1.90	1.90-1.92	1.90-1.92
Dynamic Viscosity(20°C)	NB/SH/T 0956	mm²/s	<2	2-10	10-250	250-1000	> 1000
Pour Point	GB/T 3535	°C	<-80	< -60	< -30	< -20	< -15
Boiling Point	GB/T 22226	°C	50-200	200-260	> 260	> 260	> 260
Neutralization Number(KOH)	NB/SH/T 0434	mg KOH/g	0.01	0.01	0.01	0.01	0.01

Note: The above data is typical data.

#### **Product Application:**

> Perfluoropolyether oil with low viscosity can be used as heat transfer fluids electronic cleaning fluids, electronic reliability test fluids and vapor phase soldering fluids. It is mainly used in electronics cleaning, heat transferring electronics testing and welding. It is also applied in all other circumstance requiring resistance to chemical. Perfluoropolyether with high molecular weight can be used as lubricating oil for compressors and delivery pumps for gases such as oxygen, fluorine, chlorine and hydrogen etc. It can be used as lubricants in vacuum pumps which satisfies all there requirements of using vacuum pumps in high clean electronic industry. It can also be used as additives for polymer processing, which improves polymer's fluidity and self-lubrication property, reduces wear loss, and enhances scratching resistance property.

#### **Package and Shipment:**

- > PE plastic drum, available in 1 kg, 5 kgs, 10 kgs, or according to customer' requirements.
- > It is shipped as non-dangerous liquid goods.

#### **Storage:**

- > Avoid to mix with other oils, long-term storage after sealing in a dry environment.
- > Avoid contact with aluminum chloride and other Lewis acid.

#### **Handling Precautions:**

- > It does no harm to eyes, skin, or other human organs. Please rinse excessively with running water if accidentally exposed.
- > Please do not contact this product with Lewis acid to avoid decomposing.
- > Please do not discard the waste oil and packaging uncautiously.
- > For other safety issues, please review MSDS of the product or contact sales representatives.



### **Fluoro Organic Materials**

We might adjust the grades and properties of our products without any further notices.

If the up-to-date information is needed, please contact us.

Manufacturer:

#### [Guang Zhou Office]

Unit 1006, 10th Floor, Tower B, NO.26 ChenYue Road, HaiZhu District Guang Zhou,

**CHINA** 

Tel: +86.20.8918.9425

#### [Hong Kong Office]

Unit 1101, 11th floor, Tower 1, Enterprise Squar Bldg, No. 9 Sheung Yuet Road,

Kowloon Bay, Hong Kong.

Tel: +852.2893.5300

http://www.teflus.com

E-mail: tftlimited\_xu@163.com